

PIGMENTS - SPECIAL INK FOR TECNOTOP ALIPHATIC RESINS

PIGMENTS is a mastic pigment designed for pigmentation-coloration of neutral aliphatic resins TECNOTOP 2C, TECNOTOP 2CP and TECNOTOP S-3000.

# **USES**


- Pigment dispersion for coloration of our polyurethane aliphatic resins TECNOTOP 2C and TECNOTOP 2CP(neutral version)
- For coloration of TECNOTOP S-3000, aliphatic two component cold and manual polyurea resin(only for neutral version)

NOTE: call our technical department about the application to other supports or situations

cleaning	DESMOSOLVENT
mix ratio	20%



### **COLORS**



## **GENERAL FEATURES**

- Add PIGMENTS to the container of component A of TECNOTOP, mixing (with a low-speed device), for the time necessary to obtain a colored mixture homogeneously.
- Cleaning materials are made with our solvent DESMOSOLVENT.
- It comes in approximate coloration of RAL chart.



### **PACKAGING**

Metal tins of 1 kg.

#### SHELF LIFE

12 months for each product at temperatures between 5° C and 35° C, provided it is stored in a dry place. Once the tin has been opened, the product must be used immediately.

#### **HANDLING**

Consult material and safety data sheet (MSDS), or contact our technical department.

PROPERTIES	VALUES
Density at 23°C ISO 1675	white:±1,5~2 g/cm³
Density at 23°C ISO 1675	red tile 8004: ±1,1~1,2 g/cm³
Density at 23°C ISO 1675	grey 7042: ±1,0 g/cm <sup>3</sup>
Density at 23°C ISO 1675	blue 5012: ±1,0 g/cm³ ±0,1
VOC(volatile organic compounds)	280 g/l
Appearance	pasty
Viscosity at 23°C ISO 2555	< 5.000 cps
% pigment contents	white: 65%
% pigment contents	red tile 8004: 52%
% pigment contents	grey 7042: 50%
% pigment contents	blue 5012: 45%
Particle size	<20 µm

NOTICE: While all the information presented in this document is believed to be reliable and to represent the best available data on these products, do not constitute sales specifications. The product properties may be changed without notice. NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, EXPRESS OR OTHERWISE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE. Liability of Tecnopol Sistemas and its affiliates for all claims is limited to the purchase price of the material. Products may be toxic and require special precautions in handling. User should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards. No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.

