



PRIMER PUC-1050 - TWO-COMPONENT, 100% SOLIDS POLYURETHANE RESIN AS A PRIMER (FOR LOW TEMPERATURES)

PRIMER PUC-1050 is a two-component, low viscosity 100% solid resin. It has been specifically designed to increase bonding and improve the surface leveling for the waterproofing and coating systems as TECNOCOAT, DESMOPOL, TECNOTOP, and TECNOFLOOR, **always in low ambient temperature conditions.**

USES

Polyurethane resin for the next uses:

- To apply in situations of low temperatures
- It is specially designed to increase adherence and improve the planimetry of the surfaces where the waterproofing and flooring systems TECNOCOAT, DESMOPOL, TECNOTOP and TECNOFLOOR will be applied.
- To apply on porous substrates such as concrete or mortar mainly.

NOTE: call our technical department about the application to other supports or situations

density at 23°C	1,11 ±0,05 g/cm ³
pot life at 15°C	±35~50minutes
trying time at 15°C	±2~3 hours
approx. coat consumption	± 150 g/m ²
mixing ratio (in volume)	1:1



GENERAL FEATURES

- Made up of a mixture of two polyurethane-based components (zero VOC)
- it needs a flat, clean, and dry surface, as hard as possible.
- It can be applied on porous surfaces: concrete, cement, etc. Excellent bond on porous surfaces
- It doesn't need diluting never.
- Depending on the state of the surface to be treated, unevenness, or plane level, the yield can vary between 150-300 g/sqm. in several layers.
- It can be applied with a roller, brush, or airless spray equipment (verify pot life).
- Do not apply to surfaces that are damp or exuding water coming from the interior of the substrate (water pressure due to phreatic level, condensations, leaking, etc.).
- It can be applied in combination with mineral particles (silica sand) on very uneven surfaces.



PACKAGING

Metal tins of 5 kg each.

SHELF LIFE

12 months for each product at temperatures between 5° C and 35° C, provided it is stored in a dry place. Once the tin has been opened, the product must be used immediately.

APPLICATION

- The surface must be clean and dry. If necessary, use pressurized water to remove any oil or grease residue, efflorescence, or other contaminants, as well as loose cement latencies.
- In some cases, it will be necessary to use mechanical processes to prepare the surface, as well as chemical means to clean metal surfaces.
- Mix the two components using a rod stirrer for about 2 minutes.
- Before applying, take into account the residual humidity from cleaning, that is, wait until its total evaporation or verify any humidity in the surface using a measuring device.
- Apply two or more coats of PRIMER PUc-1050 until the desired thickness is obtained.
- If the surface to be treated is very uneven, apply an initial coat of PRIMER PUc-1050 mixed with mineral filings to level it.
- Wait until completely dry before applying the desired waterproofing or concrete protection system.

HANDLING AND SAFETY

These safety recommendations for handling, are necessary for the implementation process as well as in the pre and post, on exposure to the loading machinery.

- Respiratory Protection: When handling or spraying use an air-purifying respirator.
- Skin protection: Use rubber gloves, remove immediately after contamination. Wear clean body-covering. Wash thoroughly with soap and water after work and before eating, drinking, or smoking.
- Eye / Face: Wear safety goggles to prevent splashing and exposure to particles in the air.
- Waste: Waste generation should be avoided or minimized. Incinerate under controlled conditions in accordance with local laws and national regulations.

Anyway, consult the material and safety data sheet of the product(MSDS) or contact our technical department



PROPERTIES

PROPERTIES	VALUE
Density at 23°C ISO 1675	1,11 ±0,05 g/cm ³
Viscosity at 23 °C ISO 2555	700±10 cps
Density compounds A/B A at 23°C ISO 1675	1,15 ±0,05 g/cm ³ / 1,12 ±0,08 g/cm ³
Viscosity compound A/B at 23 °C ISO 2555	50~400 cps /400~950 cps
Mixing ratio (in volume)	1:1
Solids content ISO 1768	100%
VOC(volatile organic compounds)	0
Adhesion to the concrete	>2 MPa
Pot-life at 15 °C	35~50 minutes
Tack-free time at 15 °C	±60 minutes
Drying time at 15 °C	±2~3 hours
Recoat range time at 15 °C	±3~24 hours
Ambiance application temperature range	5~35 °C
Service temperature range	15~80 °C
Max. Moisture on the support	4%
Dilution	NO

Results were performed in the laboratory at 15°C or 23°C and 50% RH, under controllable conditions. These values may vary depending on the application, climatology, or substrate conditions.

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. The customer assumes full responsibility for quality control, testing, and determination of the suitability of products for its intended application or use.

We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or law, including any warranty of merchantability or fitness for a particular purpose since Tecnopol Sistemas S.L.U. does not control the execution, since Tecnopol Sistemas S.L.U. does not control the execution. Our total liability and customers' exclusive remedy for all proven claims is the replacement of the nonconforming product and in no event shall we be liable for any other damages. While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/ use, Tecnopol Sistemas S.L.U. recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use.

No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be sued without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of Tecnopol Sistemas S.L.U. terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by Tecnopol Sistemas S.L.U. hereunder are given gratis and Tecnopol Sistemas S.L.U. assumes no obligation or liability for the description, designs, data or information is given or results obtained, all such being given and accepted at the reader's risk.

All data furnished refers to standard production using manufacturing testing tolerances. The product user, and not Tecnopol Sistemas S.L.U., is responsible for determining the suitability and compatibility of our products for the final user's intended use.

The liability of Tecnopol Sistemas S.L.U. and its affiliates for all claims is limited to the purchase price of the material.

Products may be toxic and require special precautions in handling. Users should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards.

No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.

