



TECNOCOAT H-2049 LV - LOW-VISCOSITY POLYUREA MEMBRANE FOR WATERPROOFING AND COATING

TECNOCOAT H-2049 LV is a two-component, low-viscosity, sprayable, aromatic coating suitable for waterproofing, protection, and sealing. It's made up of two high reactive liquid components, isocyanates and amines, which are mixed using our specific spray equipment (TC2049 <http://spray-equipment.tecnopolgroup.com/>) or similar, to form a solid, continuous, watertight and waterproof, seamless, high-density polyurea membrane, with mechanical qualities especially for **protecting the spray polyurethane foams systems TECNOFOAM (SPF)**.



USES

For application in the following situations:


- Flat or sloped asbestos roofs (used with TECNOFOAM, spray polyurethane foam system)
- As a protection for SPF (TECNOFOAM spray polyurethane foam system)
- Furniture and thematizations
- Vehicle and boat coatings (bed liners)
- ROOFING: Sloped/flat walkable roofs, IRMA, balconies, and overhangs
- Concrete decks, retaining walls, and foundations

NOTE: call our technical department about the application to other substrates or scopes of use

Minimum thickness	1,5 mm
Tack-free time	±20 secs
Tensile strength	±13 MPa
Elongation	>250 %
Shore A/D hardness	>85 / >45
Application method	Medium pressure spray equipment
VOC (volatile organic compounds)	0



COLORS



GENERAL SPECIFICATIONS

- Two-component, 100% solids content, low viscosity, aromatic polyurea that once applied, forms a stretchable, continuous, seamless, waterproofing, and solid membrane that offers a waterproofing and watertight behavior.
- It is also possible to apply it on flat or sloped walkable roofs, pedestrians, concrete slabs, foundation walls.
- It has **CE marking** on the basis of a statement made DoP Declaration of Performance (DoP) conforms to the UE 305/2011 regulation.
- The application and training are done by our spray equipment TC2049 (spray-equipment.tecnopolgroup.com) or similar
- Thanks to its versatility and its tack-free time of approx. 20 seconds, allows the adherence to any surface, making it the ideal product for application on uneven surfaces and in areas of any shape, whether curved or squared.
- Due to its resistance, it can be walked on and it will accept a rough finish to make it non-slip. (using Silica Sand or Tecnoelastic range aggregates)
- A ceramic floor can be placed on top. In this case, we recommend applying a thin coat of Primer PU-1000 or Primer PU-1050, consumption of around 50 to 60 g/sqm, and spreading Silica Sand on top, consumption of around 700-1000 g /sqm, to improve mechanical anchorage.
- Joints and any type of union are saved since the finish is uniform and in one piece, providing a surface with optimal maintenance and cleaning.
- His properties allow it to adhere to any surface such as concrete, ceramic tiles, metals, spray polyurethane foam (Tecnofoam), plywood(OSB), asphalt/bituminous sheets.
- In any case or material, the surface must be consistent, firm, clean, and dry when the products are applied. Recommended applying directly on the concrete deck.
- Free from harmful VOC compounds, therefore, it does not hurt the ozone layer (VOC's zero). It's 100% recyclable by mechanical means friendly to the environment; no gas collection for recycling and/or destruction is required; it doesn't emit substance to the environment once installed..
- It should be applied in dry conditions avoiding the presence of humidity or coming from the surface to be coated or the substrate, whether at the time of application or subsequently (pressure from phreatic water level). In the event there is humidity in the substrate at the time of application.
- It is an aromatic membrane and, even though it is stable against solar radiation it requires solar radiation protection (UV rays) to do not lose its physical and mechanical properties. Therefore, this system needs a protective polyurethane colored aliphatic resin, Tecnotop 2C, for use in the absence of other physical protection elements. You can apply Tecnotop S-3000, Tecnotop 2CP or Tecnotop 1C also.

PACKAGING

Metal drums of 225 kg each component (B side: resins and A side: isocyanates).

SHELF LIFE

12 months at temperatures between 5°C to 35°C, provided it is stored in a dry place, keep away from direct sunlight, extreme heat, cold, or moisture. Once the tin has been opened, the product must be used. Once opening drum, B side must be agitated mechanically before inserting the transfer pumps and use.

Concrete substrate

- Concrete should be completely cured (concrete curing takes 28 days) or, in any case, the maximum level of humidity allowed for the substrate should be verified, depending on the primer used.
- Concrete must have a surface with a correct planimetry, high surface resistance, eliminating laitance or release agents, without excessive irregularities. Therefore, the previous action of sanding, polishing, milling or shot-blasting will be assessed by the applicator to achieve a preparation of the support according to ICRI Guide



03732, CSP values 3 to 5.

- Cracks and damaged areas must be repaired using epoxy mortar Primer EP-1020/Primer EP-1010.
- Mastic PU must be used on fissures or small cracks on the surface.
- In joints (width < 15 mm): remove old material, clean and fill with Mastic PU.
- In joints (width >15 mm): remove old material, clean and fill with Mastic PU. Complement with a Tecnoband 100 band on the upper part.
- In structural/expansion joints: remove old material, clean and fill with Mastic PU. Complement with specific elastic bands and Tecnoband 100
- Clean up well and eliminate all contaminants from the elements, such as dust or chippings, using dry methods preferably.
- Primer application using our Primer PU-1050/Primer PUC-1050, total yield of 250 g/sqm (applied in several thin coats) or Primer WET depending on the existing moisture in the substrate and with a total yield of 450 g/sqm
- Apply/spray the membrane evenly and in several layers until the dry film thickness required by the project is achieved.
- Application of the aliphatic polyurethane resin for protection against UV rays Tecnotop 2C/2CP/1C

Ceramic tiles substrate

- Ceramic surfaces should not have empty joints or loose elements or parts. These should be filled with Mastic PU mastic or mortar, according to their size.
- Existing joints or seals: remove the old material, clean up and fill with Mastic PU and reinforced using Tecnomesh 100
- Sanding with specific equipment. Thereby, to remove moss or solids particles bonded to the support, and opening the pore.
- Clean up, using a vacuum method.
- Primer application using Primer EP-1040, total yield 100-150 g/sqm, or Primer EPw-1070, total yield 150-200 g/sqm
- Apply/spray the membrane evenly and in several layers until the dry film thickness required by the project is achieved.
- Application of the aliphatic polyurethane resin for protection against UV rays Tecnotop 2C/2CP/1C.

NOTE: For other types of supports, weather conditions or the substrate to be applied, consult our technical department.

REPAIR AND OVERLAPS PROCESSES

REPAIR

In cases where the membrane repair by accidental causes, or assembly procedures not covered installations, shall be as follows:

- Cut, removal of the affected area and/or damaged surface
- Sanding this area extending about 20~30 cm. around the perimeter, for overlapping security
- Cleaning (vacuuming) of waste generated (powder, dust...); if it's possible don't use water, and if used, support humidity value; ketones applicability based solvents for reducing this type of surface cleaning
- Apply a thin layer (100-150 g/sqm) of polyurethane resin Primer PU-1050/Primer EPw-1070.
- Light spread Silica Sand over the wet primer applied before
- Wait for the total drying
- Apply/spray the membrane evenly and in several layers until the dry film thickness required by the project is achieved.
- Application of the aliphatic polyurethane resin for protection against UV rays Tecnotop 2C/2CP/1C

OVERLAPS

In cases has been exceeded recoat time (24~48 hours), so the waiting time between jobs is prolonged, proceed as follows:



- Sanding strip longitudinal overlap of about 20~30 cm. wide
- Cleaning (vacuuming) of waste generated (powder, dust...) or existing dust; if it's possible, do not use water, and if it's used, check the support humidity value; ketones applicability based solvents for conducting this type of surface cleaning
- Apply a thin layer (100-150 g/sqm) of polyurethane resin Primer PU-1050/Primer EPw-1070.
- Light spread Silica Sand over the wet primer applied before
- Wait for the total drying
- Apply/spray the membrane evenly and in several layers until the dry film thickness required by the project is achieved.
- Application of the aliphatic polyurethane resin for protection against UV rays Tecnotop 2C/2CP/1C

APPLICATION REQUIREMENTS (SPRAY EQUIPMENT)

For the formation, it is necessary to mix the two initial liquid components, isocyanates and amines by our spray equipment TC2049 (spray-equipment.tecnopolgroup.com) or similar (proper maintenance and cleaning it is recommended). The general parameters for this material will be the following:

- Isocyanate heater temperature: 60-65°C (140°F to 149°F)
- Resin heater temperature: 60-65°C (140°F to 149°F)
- Hose temperature: ±65°C (149°F)
- Working pressure: 2.500 - 3.000 psi (170 to 205 bar)
- Recommended mixing chamber: GU-07008-1 or GU-07008-2

These temperatures and pressure parameters must be valued, ratified or slightly varied by the applicator, depending on the conditions of each climatic zone, weather situation or according to the specifications of the projection equipment. It is the responsibility of the owner / applicator of the equipment to keep it in perfect condition in order to maintain the correct mixing ratio of the two components that Tecnopool delivers separately, by periodically updating its maintenance controls. During the execution of the application, it may be necessary to correct these parameters according to changing external conditions, as well as to verify the correct operation of the machine (pressure and temperature).

HEALTH AND SAFETY

These safety recommendations for handling, are necessary for the implementation process as well as in the pre and post, on exposure to the loading machinery.

- Respiratory Protection: When handling or spraying use an air-purifying respirator.
- Skin protection: Use rubber gloves, remove immediately after contamination. Wear clean body-covering. Wash thoroughly with soap and water after work and before eating, drinking, or smoking.
- Eye / Face: Wear safety goggles to prevent splashing and exposure to particles in the air.
- Waste: Waste generation should be avoided or minimized.
- Incinerate under controlled conditions in accordance with local laws and national regulations.
- Re-occupancy of the work site without respiratory equipment is minimum 24 hours providing the correct ventilation for the area sprayed.
- Contractors and applicators must comply with all applicable and appropriate guidelines for storage and safety guidelines.

Anyway, consult the material and safety data sheet of the products of the system.

COMPLEMENTARY PRODUCTS

The following products can be applied as complements to their use. In this way, its physical-mechanical characteristics are protected and improved depending on its exposure, desired finish, or type of substrate:



- PRIMER EP-1010: epoxy resin with charges for filling existing holes in concrete or ceramic surfaces, to be applied in a single coat
- PRIMER EP-1020: epoxy resin to apply on concrete or ceramic substrates, improving adherence, absorbing substrate moisture, and regularizing the planimetry of the substrate.
- PRIMER PU-1050/PUc-1050: solvent-free polyurethane resin to apply on concrete, improving adherence, absorbing substrate moisture, and regularizing the planimetry of the substrate.
- PRIMER EP-1040: epoxy resin to apply on metal or ceramic substrates, improving adherence, absorbing substrate moisture, and regularizing the planimetry of the substrate
- PRIMER EPw-1070: water-based epoxy resin to apply on concrete, asphalt, metal, or ceramic substrates, absorbing substrate moisture and regularizing the planimetry of the substrate.
- PRIMER WET: epoxy resin to apply on very wet concrete or ceramic substrates, improving adherence, absorbing substrate moisture, and regularizing the planimetry of the substrate.
- TECNOTOP 2C: two-component, glossy, and colored aliphatic polyurethane resin, to protect walkable and vehicular roofs and floors against UV rays when there is no other protection.
- TECNOTOP 2CP: two-component, glossy, and colored aliphatic polyurethane resin to protect against UV rays and chlorinated/salted water in swimming pools, lakes, and aquariums when there is no other protection.
- TECNOTOP 1C: single-component, glossy, and colored aliphatic, for non-walkable/maintenance roofs against UV rays when there is no other protection
- TECNOTOP S-3000: two-component, polyaspartic, aliphatic, colored, fast-curing resin for coating for protection against UV rays, quick dry time, and excellent chemical and mechanical characteristics.
- TECNOPLASTIC F/C: plastic particles (two different weights) that, once mixed, form a rough surface, even complying with the CTE DB SUA1 (Slipperiness of floors), until achieving a CLASS 3 classification (Rd>45) UNE-ENV 12633:2003, according to its dosage (ask our technical department).
- TECNOBAND 100: cold bond deformable band made up of an upper layer of non-woven textile and a lower layer of viscoelastic self-adhesive coating, which together allow it to adapt to the shape of the substrate. This band is ideal when dealing with structural joints and overlapping metal materials.
- TECNOMESH 200 BASE: non-woven woven for previous placement on excessively irregular substrates or in areas of earth or natural substrate.
- MASTIC PU: polyurethane mastic for filling joints (use together with Tecnoband 100 when necessary).

TECHNICAL DATA OF COMPONENTS

PROPERTIES	COMPONENT A	COMPONENT B*
Density ISO 1675	1,10±0,05 g/cm ³	1,09 ±0,05 g/cm ³
Viscosity (at 12 rpm) ISO 2555	300±50 cps	8000±50 cps
Mix ratio – in weight	100	102
Mix ratio – in volume	100	100

* Data for component B pigmented in gray. For other colorations or neutral, consult the official COA issued by Tecnopól (Certificate of Analysis for each batch delivered). Results were performed in the laboratory at 23°C and 50% RH, under controllable conditions.



TECHNICAL FEATURES

PROPERTIES	RESULTS
Density ISO 1675	1,15 g/cm ³ ±0,03 g/cm ³
Tack-free time	±20 secs
Recoat time	20 secs ~ 48 hours
Use temperature range (environment)	-10 °C ~ 90 °C (14°F to 194°F)
Application temperature range (substrate and environment)	5 °C~ 35 °C (41°F to 95°F)
Maximum environmental humidity	±80%
Elongation at break ISO 527-3	>250%
Tensile Strength ISO 527-3	>13 MPa
Hardness Shore A/D DIN 53.505	>85 / >45
VOC content(volatile organic compounds)	0
Solid Content ISO 1768	100%
Construction element slope	zero slope, ponding water admitted
	100%
Adherence to concrete	> 1,5 MPa
Fire reaction	NPA

Results performed in the laboratory at 25°C (73°F) and 50% RH, under controllable conditions. These values may vary depending on the application, climatology, or substrate conditions.

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. The customer assumes full responsibility for quality control, testing, and determination of the suitability of products for its intended application or use.

We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or law, including any warranty of merchantability or fitness for a particular purpose since Tecnopol Sistemas S.L.U. does not control the execution, since Tecnopol Sistemas S.L.U. does not control the execution. Our total liability and customers' exclusive remedy for all proven claims is the replacement of the nonconforming product and in no event shall we be liable for any other damages. While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/ use, Tecnopol Sistemas S.L.U. recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use.

No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be sued without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of Tecnopol Sistemas S.L.U. terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by Tecnopol Sistemas S.L.U. hereunder are given gratis and Tecnopol Sistemas S.L.U. assumes no obligation or liability for the description, designs, data or information is given or results obtained, all such being given and accepted at the reader's risk.

All data furnished refers to standard production using manufacturing testing tolerances. The product user, and not Tecnopol Sistemas S.L.U., is responsible for determining the suitability and compatibility of our products for the final user's intended use.

The liability of Tecnopol Sistemas S.L.U. and its affiliates for all claims is limited to the purchase price of the material.

Products may be toxic and require special precautions in handling. Users should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards.

No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.

