



TECNOFOAM G-2008 - SPRAY POLYURETHANE FOAM (SPF) SYSTEM FOR THERMAL INSULATION (APPLIED DENSITY $\pm 8\sim 12$ KG/M³)

TECNOFOAM G-2008, spray polyurethane open-cell foam system (SPF) for and thermal and acoustic insulation, is specifically formulated to apply low-density foam ($\pm 8\sim 12$ kg/m³). Its application must be carried out by the specific reactor equipment by mixing Tecnofoam G-2008 (polyol side) and Tecnofoam G-2049.I (isocyanate side). The blowing agent is water.

It has CE marking on the basis of a statement made DoP Declaration of Performance (DoP) under the European Norm EN-14315-1:2031.



USES

The spray polyurethane foam system TECNOFOAM G-2008 can be used in these situations:


- application continuous thermal insulation systems in residential buildings, businesses or industries
- indoor applications ceilings, interior chambers facade, ventilated facades, internal side of roofs, made with wood structure, or other material (see compatibility)

NOTE: For other applications/situations, please, consult our technical department

applied density	$\pm 8\sim 12$ kg/m ³
thermal conductivity	0,039 W/m·K
cream time at 20°C	4~8 secs
gel time at 20°C	8~13 secs
tack-free time at 20°C	13~17 secs
reaction to fire	Euroclass F ¹
emissions(VOC)	A+aC
application	spray equipment



COLORS



Yellow



GENERAL FEATURES

- TECNOFOAM G-2008 is a product with high thermal insulating capacity, easy to apply and to protect all the internal surfaces of the building
- the application and training is done by our spray equipment TC2049 (spray-equipment.tecnopolgroup.com) or similar
- it forms a continuous coat without joints preventing the formation of "heat bridges" and providing an optimum thermal insulation surface with high thermal insulation parameters
- the blowing agent is water
- it is free from harmful to the ozone layer, so do not promote the greenhouse effect (NOT contain HFCs, HCFCs, VOCs, etc ...); it does not emit any substance to the environment once installed
- TECNOFOAM G-2008 system is 100% recyclable by mechanical means friendly to the environment
- no gas collection for recycling and/or destruction is required
- the thermal conductivity (?) coefficient remains unchanged from the application and along with the product life.
- the properties of the polyurethane foam system TECNOFOAM G-2008 allow it to adhere to any surface such as concrete, ceramic, metal, polyurethane foam, wood, acrylic paints (checking the situation of areas recommended).
- It is regulated under the European standard EN 14315-1: 2013 "Thermal insulating products for applications in buildings, rigid polyurethane foam (PUR) products", for which it has CE marking based on a DoP Declaration of Performance.

YIELD

The performance is around 1kg/m² at 10 cms of thickness.

PACKAGING

Metal drums of 215 kg for the polyol, and 250 kg for the isocyanate.

SHELF LIFE

POLYOL COMPOUND: 4 months (we recommend stirring before use)

ISOCYANATE COMPOUND: 6 months

Temperature within 5 °C ~ 35 °C, provided it is stored in a dry place, with no direct contact with the sun.

APPLICATION METHOD

In general, you should take the following factors:

- the application of polyurethane foam system TECNOFOAM G-2008 should be performed under non-presence of moisture or water from the support stand on which to apply either at the time of application as a posteriori.
- the substrate must be clean and free of dust
- in applications with high-temperature gradients a vapor barrier is placed on the warm side of the insulation to prevent condensation
- metal surfaces should be protected with an anti-corrosive primer before being coated with foam. On smooth surfaces without pores, galvanized steel, polypropylene, etc ... a secure grip primer should be applied
- to apply in one direction to achieve the expansion which is about 10 ~ 12 cm.
- if necessary, and once fully expanded, apply a second layer on the already initially applied.
- its great expansion causes sometimes have to cut the excess with the help of a saw
- TECNOFOAM G-2008 adheres firmly to most common materials such as wood, plasterboard, steel, OSB,



- plywood, cement, inside masonry exterior plaster panels, and construction itself.
- reactivity times (in laboratory conditions):
 - REACTING TIME: 4 seconds
 - EXPANDING TIME: 8 seconds

APPLICATION REQUIREMENTS (SPRAY EQUIPMENT)

For the formation, it is necessary to mix the two initial liquid components, isocyanates and polyols with our spray equipment TC2049 (spray-equipment.tecnopolgroup.com) or similar (proper maintenance and cleaning it is recommended).

The general parameters for this material will be the following:

- Heater isocyanate temperature: $\pm 40-45$ °C
- Heater polyol temperature: $\pm 45-55$ °C
- Hose temperature: $\pm 45-50$ °C
- Pressure: 1.700-2.000 psi

These temperature and pressure parameters have to be valued, ratified, or be varied by the applicator, depending on the conditions of each climate zone, weather situation, or projection equipment specifications.

HANDLING

These safety recommendations for handling, are necessary for the implementation process as well as in the pre-and-post, on exposure to the loading machinery.

- Respiratory Protection: When handling or spraying use an air-purifying respirator.
- Skin protection: Use rubber gloves, remove immediately after contamination. Wear clean body-covering. Wash thoroughly with soap and water after work and before eating, drinking, or smoking.
- Eye / Face: Wear safety goggles to prevent splashing and exposure to particles in the air.
- Waste: Waste generation should be avoided or minimized.
- Incinerate under controlled conditions in accordance with local laws and national regulations.

Anyway, consult the safety data sheet of the product, which is publicly available.

COMPOUND CHARACTERISTICS

characteristic	POLYOL	ISOCYANATE(MDI)
Viscosity at 20°C BROOKFIELD VISCOSIMETER	290mPa.s	210 mPa.s
NCO content ISO 14896	---	31 %
Specific weight at 20°C	1,09 g/cm ³	1,23 g/cm ³
Mix ratio by volume at 20°C	100	100
Mix ratio by weight at 20°C	100	109



APPLIED SYSTEM CHARACTERISTICS (REACTION)

CHARACTERISTIC	VALUE
Stirring time at 20°C	4~8 secs
Gel time at 20°C	8~13 secs
Tack-free time at 20°C	13~17 secs
Density free rise at 20°C	8 kg/m ³
Closed-cell content ASTM 2856	<15% (CCC1)
Thermal conductivity value at 20°C EN-12667	0,039 W/mK
GWP(Global Warming Potential)	1
ODP (Ozone Depletion Potential)	0
VOC (volatile organic compounds) ISO 16000-6	Class A+aC
Fire reaction EN-13501	Euroclass F ¹
Acoustic test	-40db in 195mm (thickness)

To obtain more information, consult the full document Declaration of Performances of a particular system (consult our technical department).

VOC EXPOSITIONS TABLE:

Component	N° CAS	C exp at 28 days	Class
formaldehyde	50-00-0	8	A+
acetaldehyde	75-07-0	5	A+
toluene	108-88-3	1	A+
tetrachloroethylene	127-18-4		A+
xylene	108-38-3	<1	A+
1,2,4-trimethylbenzene	95-63-6	0	A+
1,4-dichlorobenzene	106-46-7		A+
ethylbenzene	100-41-4		A+
2-butoxyethanol	111-76-2		A+
Styrene	100-42-5	1	A+
TCOV	---	1011	A
Resulting emission class			A

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. The customer assumes full responsibility for quality control, testing, and determination of the suitability of products for its intended application or use.

We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or law, including any warranty of merchantability or fitness for a particular purpose since Tecnopol Sistemas S.L.U. does not control the execution, since Tecnopol Sistemas S.L.U. does not control the execution. Our total liability and customers' exclusive remedy for all proven claims is the replacement of the nonconforming product and in no event shall we be liable for any other damages. While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/ use, Tecnopol Sistemas S.L.U. recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use.

No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be sued without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of Tecnopol Sistemas S.L.U. terms and conditions



of sale. Further, the descriptions, designs, data, and information furnished by Tecnopol Sistemas S.L.U. hereunder are given gratis and Tecnopol Sistemas S.L.U. assumes no obligation or liability for the description, designs, data or information is given or results obtained, all such being given and accepted at the reader's risk.

All data furnished refers to standard production using manufacturing testing tolerances. The product user, and not Tecnopol Sistemas S.L.U., is responsible for determining the suitability and compatibility of our products for the final user's intended use.

The liability of Tecnopol Sistemas S.L.U. and its affiliates for all claims is limited to the purchase price of the material.

Products may be toxic and require special precautions in handling. Users should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards.

No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.

