



**TECNOFOAM G-2040 HFO - SPRAY
POLYURETHANE FOAM (SPF) SYSTEM FOR
THERMAL INSULATION(APPLIED DENSITY ± 40
KG/M³)**

TECNOFOAM G-2040 HFO, spray polyurethane foam system (SPF) for thermal insulation is specifically formulated to apply foam with applied density around (± 40 – 46 kg/m³). Its application must be carried out by the specific reactor equipment by mixing Tecnofoam G-2040 HFO (polyol side) and Tecnofoam G-2049.I (isocyanate side). The blowing agent is HFO gas.

It has CE marking on the basis of a statement made DoP Declaration of Performance (DoP) under the European Norm EN-14315-1:2031.



USES

The spray polyurethane foam system TECNOFOAM G-2040 HFO can be used in these situations:

- a complete and continuous system of thermal insulation in construction, industrial, farming, or agricultural facilities.
- in applications where flat roofs, interior floor
- installations with floor heating system, all those with high compression needs on the surface

NOTE: For other applications/situations, please, consult our technical department

applied density at 23°C	40 ~ 46 kg/m ³
initial thermal conductivity at 23°C	0,022 W/m-K
stirring time at 20°C	2 ~4 secs
gel time at 20°C	4 ~ 11 secs
tack-free time at 20°C	12 ~ 14 secs
close cell content	>95%(CCC4)
fire reaction	Euroclass E
mix ratio (vol.)	100/100
application method	spray equipment



COLORS

	Yellow
---	--------



GENERAL FEATURES

- TECNOFOAM G-2040 HFO is a product with high insulating capacity, easy to apply to cover all surfaces using our spray equipment TC2049 (spray-equipment.tecnopolgroup.com) or similar
- it forms a continuous coat without joints preventing the formation of "heat bridges" and providing an optimum thermal insulation surface with high thermal insulation parameters
- the blowing agent is HCFO-1233zd(E). This gas has a low rating GWP(=1)(Global Warming Potential)
- it doesn't contain HCFC, HFC.
- TECNOFOAM G-2040 HFO system is 100% recyclable by mechanical means friendly to the environment
- it does not emit any substance to the environment once installed.
- the properties of this polyurethane foam system allow it to adhere to any surface such as concrete, ceramic, metal, polyurethane foam, wood, acrylic paints (checking the situation of areas recommended).
- the application of TECNOFOAM G-2040 HFO is completely continuous, instead of the classic non-continuous thermal insulation material, saving any kind of union between applications, and providing an optimum thermal insulation surface with high thermal insulation parameters
- It is regulated under the European standard EN 14315-1: 2013 "Thermal insulating products for applications in buildings, rigid polyurethane foam (PUR) products", for which it has CE marking based on a DoP Declaration of Performance.

PACKAGING

Metal drums of 250 kg for the isocyanate and 230 kg for the polyol side

SHELF LIFE

POLYOL COMPOUND: 3 months

ISOCYANATE COMPOUND: 6 months

Always store the drums before use at a temperature between 5 °C and 35 °C, always in dry areas, without the possibility of humidity entry, and without direct contact with the sun or sources of heat. Very low temperatures increase the viscosity of the polyol which makes it difficult to mix and apply, and in the isocyanate, they can generate crystallisations, which can cause its mixing ratio to vary and the consequent internal problems in the mixing and application equipment.

Very high temperatures can modify polyols, causing loss of the blowing agent, increasing consumption and producing the swelling of the metallic drum. To avoid these last situations, it is recommended to let the drums for a while before use, in a cool and ventilated place.

APPLICATION METHOD

In general, you should take the following factors:

- the application of polyurethane foam system TECNOFOAM G-2040 HFO should be performed under the non-presence of moisture or water from the support stand on which to apply either at the time of application as a posteriori.
- the substrate must be clean and free of dust
- minimum recommended surface temperature: 5°C
- in applications with high-temperature gradients, a vapor barrier is placed on the warm side of the insulation to prevent condensation
- perform successive layers of a thickness 2~3 cm each one
- wait to apply the second layer, until minimum temperature on the first layer 40-50°C
- TECNOFOAM G-2040 adheres firmly to most common materials such as wood, plasterboard, steel, OSB,



- plywood, cement, inside masonry exterior plaster panels, and construction itself.
- no shrinkage after performing the expansion.
- reactivity times (in laboratory conditions):
 - REACTING TIME: 3-5 seconds
 - EXPANDING TIME: 9-12 seconds

APPLICATION REQUIREMENTS (SPRAY EQUIPMENT)

For the formation, it is necessary to mix the two initial liquid components, isocyanates and polyols with our spray equipment TC2049 (spray-equipment.tecnopolgroup.com) or similar (proper maintenance and cleaning it is recommended).

The general parameters for this material will be the following:

- Heater isocyanate temperature: $\pm 40-45$ °C
- Heater polyol temperature: $\pm 52-57$ °C
- Hose temperature: $\pm 40-50$ °C
- Pressure: 1.700-2.000 psi (120 to 140 bar)
- Mixing chamber (recommended): GU-07008-2

These temperature and pressure parameters have to be valued, ratified, or be varied by the applicator, depending on the conditions of each climate zone, weather situation, or projection equipment specifications.

HANDLING

These safety recommendations for handling, are necessary for the implementation process as well as in the pre and post, on exposure to the loading machinery.

- Respiratory Protection: When handling or spraying use an air-purifying respirator.
- Skin protection: Use rubber gloves, remove immediately after contamination. Wear clean body-covering. Wash thoroughly with soap and water after work and before eating, drinking, or smoking.
- Eye / Face: Wear safety goggles to prevent splashing and exposure to particles in the air.
- Waste: Waste generation should be avoided or minimized.
- Incinerate under controlled conditions in accordance with local laws and national regulations.

Anyway, consult the material and safety data sheet of the product.

COMPLEMENTARY PRODUCTS

The TECNOFOAM system may be complemented with the following products as a means of protection or to improve its physical-mechanical properties depending on its exposure, the desired finish, or the type of substrate.

TECNOCOAT 2049 LV: pure low viscosity polyurea. Approximate consumption 1,5 kg/m²

DESMOPOL: single component polyurethane membrane for waterproof. Approximate consumption 1,5 ~ 2 kg/m²

TECNOTOP 1C/2C: colored aliphatic resin used to protect against UV rays, to use after DESMOPOL or TECNOCOAT membranes



COMPOUND CHARACTERISTICS

characteristic		POLYOL	ISOCYANATE(MDI)
Nº OH	DIN 53240-2	280 mgKOH/g	----
Viscosity at 25°C	BROOKFIELD VISCOSIMETER	<600 mPa.s	210 mPa.s
Water content	ISO 14897	1,8 %	-----
NCO content	ISO 14896	---	31 %
Specific weight at 25°C		1,20 g/cm ³	1,23 g/cm ³

APPLIED SYSTEM CHARACTERISTICS (REACTION)

CHARACTERISTIC	VALUE
Stirring time at 20°C	2 ~4 seg
Gel time at 20°C	4 ~11 seg
Tack-free time at 20°C	12~14 seg
Density free rise at 20°C	32 ~36 kg/m ³
Closed-cell content ASTM 2856	>95% (CCC4)
Compressive strength	>300 KPa
Aged thermal conductivity value at 23°C EN-12667	0,028 W/mK
GWP(Global Warming Potential)	1
ODP (Ozone Depletion Potential)	0
VOC (volatile organic compounds) ISO 16000-6	Class C (2084 µg/m3)
Fire reaction EN-13501	Euroclass E

To obtain more information, consult the full document Declaration of Performances of the particular system (consult our technical department).

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. The customer assumes full responsibility for quality control, testing, and determination of the suitability of products for its intended application or use.

We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or law, including any warranty of merchantability or fitness for a particular purpose since Tecnopol Sistemas S.L.U. does not control the execution, since Tecnopol Sistemas S.L.U. does not control the execution. Our total liability and customers' exclusive remedy for all proven claims is the replacement of the nonconforming product and in no event shall we be liable for any other damages. While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/ use, Tecnopol Sistemas S.L.U. recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use.

No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be sued without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of Tecnopol Sistemas S.L.U. terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by Tecnopol Sistemas S.L.U. hereunder are given gratis and Tecnopol Sistemas S.L.U. assumes no obligation or liability for the description, designs, data or information is given or results obtained, all such being given and accepted at the reader's risk.

All data furnished refers to standard production using manufacturing testing tolerances. The product user, and not Tecnopol Sistemas S.L.U., is responsible for determining the suitability and compatibility of our products for the final user's intended use.

The liability of Tecnopol Sistemas S.L.U. and its affiliates for all claims is limited to the purchase price of the material.

Products may be toxic and require special precautions in handling. Users should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards.

No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.

