



TECNOMESH 200 BASE - POLYPROPYLENE MESH

Tecnomesh 200 Base is a non-woven mesh made of 100% polypropylene fibers, heat-set on one side, and calendered on the other, with a mass of 200 g/m², offered in rolls. Is a specific material to be used in Tecnocoat application where the substrate is very irregular or on the soil.

USES

For use in these types of situations:

- Formation of ponds or lakes on land or natural substrate (soil)
- Creation of a substrate able to be applied by Tecnocoat membranes in concrete substrates in bad conditions (such a foundation slabs or floors).
- In existing supports of asphalt sheets with cracks and very deteriorated.d.

NOTE: call our technical department about the application to other supports or situations

Mass	200 g/m ²
Average thickness	1,40 mm.
Transverse resistance	800 N
Longitudinal resistance	330 N
Transverse elongation	55%
Longitudinal elongation	60%

APPLICATION METHODOLOGY

- Spread and nail the mesh directly to the support using wide-head cloves.
- Make overlaps between layers of between 10-15 cms. to achieve homogenization of the surface, therefore, the maximum cohesion of the whole rolls
- Apply Tecnocoat on the Tecnoband 200 Base joints first.
- Apply Tecnocoat, on the rest of the surface according to the total desired thickness on the project.

PACKAGING

Roll of 105 m². Measures: 1,50 m. wide and 70 m. of length



The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. The customer assumes full responsibility for quality control, testing, and determination of the suitability of products for its intended application or use.

We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or law, including any warranty of merchantability or fitness for a particular purpose since Tecnopol Sistemas S.L.U. does not control the execution, since Tecnopol Sistemas S.L.U. does not control the execution. Our total liability and customers' exclusive remedy for all proven claims is the replacement of the nonconforming product and in no event shall we be liable for any other damages. While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/ use, Tecnopol Sistemas S.L.U. recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use.

No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be used without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of Tecnopol Sistemas S.L.U. terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by Tecnopol Sistemas S.L.U. hereunder are given gratis and Tecnopol Sistemas S.L.U. assumes no obligation or liability for the description, designs, data or information is given or results obtained, all such being given and accepted at the reader's risk.

All data furnished refers to standard production using manufacturing testing tolerances. The product user, and not Tecnopol Sistemas S.L.U., is responsible for determining the suitability and compatibility of our products for the final user's intended use.

The liability of Tecnopol Sistemas S.L.U. and its affiliates for all claims is limited to the purchase price of the material.

Products may be toxic and require special precautions in handling. Users should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards.

No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.

