



**TECNOTOP S-3000 HR - TWO COMPONENT, HI-TECH COLORED, HIGH RESISTANCE, COLD POLYUREA BASED RESIN FOR HIGH QUALITY COATINGS**

TECNOTOP S-3000 HR is a two component, fluid, aliphatic and pigmented coating; with high mechanical resistance, cold application by a roll. Suitable for pavement and floor finishing (suitable for low external temperatures).



## USES

Flooring resin to use on the next situations:

- Pavements of heavy and intense traffic as for garages, car parks, malls.
- Pavements of high decontamination and cleaning requirements as in chemical and food industries

**NOTE:** call our technical department about the application to other supports or situations

density at 23°C	±1,60 g/cm <sup>3</sup>
tensile strength at 23 °C	>11 MPa
shore A at 7 days at 23 °C	>98
solid content	100%
recoat time at 23 °C	±1,5~2 hours
concrete adhesion	>2 MPa
passable (pedestrian) at 23°C	±2 hours
passable (pedestrian) at -20°C	±8 hours
passable (light vehicles) at 23°C	±8~12 hours



## COLORS

	Neutral
	Grey RAL 7042
	RAL



## GENERAL FEATURES

- Aliphatic, fast dry coating ( $\pm 2$  hours to allow the pedestrian walk)
- Cold application by roll
- Application at low ambient temperatures (dry time 8 hours at  $-20^{\circ}\text{C}$ )
- 100% solids content
- Excellent resistance to heavy traffic, outside (aliphatic behavior) and inside areas
- It can be applied on several supports: concrete, ceramic tiles, cement or DESMOPOL, and TECNOCOAT waterproofing aromatic membranes
- TECNOFLOOR S-3000 HR should be applied in dry conditions avoiding the presence of humidity or water coming from the surface to be coated or the substrate, whether at the time of application or subsequently (pressure from phreatic water level)
- In the event there is humidity in the substrate at the time of application, consult the technical specifications of our primers where the maximum humidity ranges are specified
- Finishing versatility, multi-layer or may be applied as a paint
- Easy of maintenance, cleaning, and decontamination
- The final product is obtained by mixing 100% of the two components. If only part of the product is used, make sure that this ratio is always maintained to ensure that the final result retains the product's best qualities.
- Mix both components together well using a rod stirrer for around 2 minutes, or until the two components are completely mixed.
- Can be used outdoors and indoors situations (aliphatic behavior)
- It is recommended that the same batch number is used in each area of application to ensure an even color is obtained
- Do not add water in any case
- You can add DESMOSOLVENT (max. 5%) for an easier application
- No solvent, odorless

## PACKAGING

Metal tins, on these two different formats:

- LARGE: 16 kg + 4 kg
- SMALL: 4 kg + 1 kg

## SHELF LIFE

12 months at temperatures between  $5^{\circ}\text{C}$  and  $35^{\circ}\text{C}$ , provided it is stored in a dry place. Once the tin has been opened, the product must be used immediately.

## APPLICATION METHOD

In general, you should take the following factors:

- repair the surface (fill in depressions, eliminate unevenness, eliminate any old waterproofing, etc.)
- singular points preparation (perimeter, sinks / evacuations, expansion joints or structural)
- clean up the surface or substrate, removing any dust, dirt, grease or efflorescence.
- the surface has to be enough compressive strength of adhesion of the membrane. If it were not so, we will proceed to apply our primers resins to achieve this target
- in case of doubt of all above, apply before in a restricted area and to check

TECNOTOP S-3000 HR can be applied to many different surfaces and the procedure will vary depending on its nature or state. Below we set out some of the applications for the most common surfaces; for other surfaces not described,



please contact our technical department.

#### Cement or concrete surfaces

- any depressions or voids should be repaired using a mix (ratio of  $\pm 1:4$ ) of our epoxy resin PRIMER EP-1020 mixed with silica sand.
- fill joints with MASTIC PU, polyurethane mastic
- the concrete should be completely cured (concrete curing takes 28 days) or, in any case, the maximum level of humidity allowed for the substrate should be verified, depending on the primer used.
- any concrete latencies or release agents should be eliminated and an open-pore surface achieved by grit blasting, milling, or sanding.
- clean up the surface or substrate, removing any dust, dirt, grease, or efflorescence.
- apply PRIMER EP-1020 100% solids epoxy resin, with a yield of approximately  $\pm 300 \text{ g/m}^2$  (two thin layers) always depending on the state of the substrate or the surface's porosity.
- application by short hair roll, thin coats of TECNOTOP S-3000 HR, recommended two layers.(consumption  $\pm 250 \text{ g/m}^2/\text{coat}$ )

#### Ceramic substrate

- light polish of surface: to open the pore, clean up of dust and dirt particles.
- ceramic surfaces should not have empty joints or loose elements or parts. These should be filled with MASTIC PU mastic, complemented with TECNOBAND 100 on the joints if necessary, or with our resin mortar made by a mix of our 100% solid content epoxy resin PRIMER EP-1020 and SILICA SAND (ratio of  $\pm 1:4$ ).
- clean up the surface
- next, apply the required primer; in these cases of non-porous surfaces use the water-based epoxy PRIMER EPw-1070, yield  $250 \text{ g/m}^2$ .
- application by short hair roll, thin coats of TECNOTOP S-3000 HR, recommended two layers.(consumption  $\pm 200 \text{ g/m}^2/\text{coat}$ )

For another kind of support contact our technical department. Please, check all the TDS of our products and systems

#### Notes:

- Consult in all cases the waiting times, drying time, singular points treatment, conditions of application of all the products through the technical data sheets of each product, the technical handbook of application of TECNOCOAT , or consult our technical department.
- For other types of supports/substrates, for further information on the execution application procedure, for any additional questions, please, consult the technical data sheets (TDS) of these products, or our technical department.
- These guidelines are valid although they can be modified, according to the situation of the supports, conditioning of the bearing structures of the elements to be waterproofed, external climatology or situation at the time of application

## APPLICATION METHODS

This is the methodology for the application of TECNOTOP S-3000 HR:

#### as a paint

- apply TECNOTOP S-3000 HR by a short-haired roller in at least two successive layers as drying times. Consumption in this type of application is  $\pm 200\text{-}250 \text{ g/m}^2/\text{layer}$ , depending on the roughness of the substrate.

#### multilayer system(SILICA SAND)

- apply a first coat of TECNOTOP S-3000 HR by short hair roll



- spread SILICA SAND on the wet surface of TECNOTOP S-3000 HR.
- once dried, remove the non bonded SILICA SAND
- apply a second coat of TECNOTOP S-3000 HR with rubber
- the last coat, applied by roll

## COMPLEMENTARY PRODUCTS

The TECNOTOP S-3000 HR system may be complemented with the following products as a means of protection or to improve its physical-mechanical properties depending on its exposure, the desired finish or the type of substrate.

- PRIMER EP-1010: 100% solids, two-component, fillerized epoxy resin, to fill in depressions in concrete surfaces, one coat application so, rapidly providing a firm and fast drying even base.
- PRIMER EP-1020: mixed with silica sand in a ratio of  $\pm 1:4$ , or calcium carbonate in ratio  $\pm 1:2$ , this is used to fill in depressions in concrete surfaces, rapidly providing a firm and fast drying even base.
- PRIMER PU-1050/PRIMER EPw-1070/PRIMER PUC-1050/PRIMER PU-1000: these several resins are applied on the substrate beforehand to improve bonding and level the surface, as well as regulating the humidity in the substrate (see permitted levels in their technical specifications). Consumption may vary depending on the type of support, nature, or surface texture. Consult the technical specifications of each product or our technical department.
- TECNOBAND 100: the cold bond deformable band made up of an upper layer of non-woven textile and a lower layer of viscoelastic self-adhesive coating, which together allow it to adapt to the shape of the substrate. This band is ideal when dealing with structural joints and overlapping metal materials.
- MASTIC PU: polyurethane mastic for filling joints (use together with TECNOBAND 100 when necessary).

## HANDLING

These safety recommendations for handling are necessary for the implementation process as well as in the pre and post, on exposure to the loading machinery.

- Respiratory Protection: When handling.
- Skin protection: Use rubber gloves, remove immediately after contamination. Wear clean body-covering. Wash thoroughly with soap and water after work and before eating, drinking, or smoking.
- Eye / Face: Wear safety goggles to prevent splashing and exposure to particles in the air.
- Waste: Waste generation should be avoided or minimized. Incinerate under controlled conditions in accordance with local laws and national regulations.

Anyway, consult the material and safety data sheet of the product (MSDS) or contact our technical department.



## TECHNICAL DATA

PROPERTIES	RESULT
Density at 23°C ISO 1675	±1,60 g/cm <sup>3</sup>
Solids content ISO 1768	100%
VOC(volatile organic compounds)	0
Viscosity at 23 °C ISO 2555	250 cps
Mixing ratio	1:4
Tensile strength at 23 °C ISO 527-3	>11 MPa
Elongation at break at 23 °C ISO 527-3	> 60%
Hardness Shore A at 7 days DIN 53.505	>97
Hardness Shore D at 7 days DIN 53.505	>60
Pot life at 23 °C	±30 minutes
Tack free time at 23 °C	±40 minutes
Recoat time at 23 °C	±1,5~2,5 hours
Environment and support range temperature (application)	-0 °C~30 °C
Environment range use temperature (service)	-20°C~65°C
Passable (pedestrian) at 23°C	±2 hours
Passable (pedestrian) at -20°C	±8~12 hours
Passable (light vehicles) at 23°C	±8~12 hours
Fire reaction EN-13501-1:2007+A1:2010	Bfl- s1
Concrete adherence	>2 MPa

These values in this table are approximate and can vary depending on the situation of the carrier or application methodology employed

The information herein is to assist customers in determining whether our products are suitable for their applications. Our products are only intended for sale to industrial and commercial customers. The customer assumes full responsibility for quality control, testing, and determination of the suitability of products for its intended application or use.

We warrant that our products will meet our written liquid component specifications. We make no other warranty of any kind, either express or implied, by fact or law, including any warranty of merchantability or fitness for a particular purpose since Tecnopol Sistemas S.L.U. does not control the execution, since Tecnopol Sistemas S.L.U. does not control the execution. Our total liability and customers' exclusive remedy for all proven claims is the replacement of the nonconforming product and in no event shall we be liable for any other damages. While descriptions, designs, data and information contained herein are presented in good faith and believed to be accurate, they are provided for guidance only. Because many factors may affect processing or application/ use, Tecnopol Sistemas S.L.U. recommends that the reader make tests to determine the suitability of a product for a particular purpose prior to use.

No warranties of any kind, either expressed or implied, including warranties of merchantability or fitness for a particular purpose, are made regarding products described or designs, data or information set forth, or that the products, designs, data or information may be sued without infringing the intellectual property rights of others. In no case shall the descriptions, information, data or designs provided be considered a part of Tecnopol Sistemas S.L.U. terms and conditions of sale. Further, the descriptions, designs, data, and information furnished by Tecnopol Sistemas S.L.U. hereunder are given gratis and Tecnopol Sistemas S.L.U. assumes no obligation or liability for the description, designs, data or information is given or results obtained, all such being given and accepted at the reader's risk.

All data furnished refers to standard production using manufacturing testing tolerances. The product user, and not Tecnopol Sistemas S.L.U., is responsible for determining the suitability and compatibility of our products for the final user's intended use.

The liability of Tecnopol Sistemas S.L.U. and its affiliates for all claims is limited to the purchase price of the material.

Products may be toxic and require special precautions in handling. Users should obtain detailed information on toxicity, together with proper shipping, handling and storage procedures, and comply with all applicable safety and environmental standards.

No freedom from any patents or other industrial or intellectual property rights is granted or to be inferred.

