

## DECLARATION OF PERFORMANCE

### N. CPR-ES2/0002

<b>1 Unique identification code of the product-type</b>	<b>TECNOCOAT CP-2049 PLUS SYSTEM</b>
<b>2 Intended uses</b>	Two-component polyurea system for intended use as a roof waterproofing
<b>3 Manufacturer</b>	TECNOPOL SISTEMAS, S.L.U. Finlàndia, 33 08520 Les Franqueses del Vallès – Barcelona-Spain www.tecnopolgroup.com – t. +34 935682111
<b>4 Systems of AVCP</b>	System 3
<b>5 Harmonized standards</b>	EAD 030350-00-0402
<b>Notified bodies</b>	The notified body Instituto de Ciencias de la Construcción Eduardo Torroja, N 1219, carried out the assessment of the performance according to the ETAG 005, edition March 2004 guideline for European Technical Approval used according to CPR 305/2011 art. 66, 3rd subsection.
<b>6 Performances declared</b>	
Essential characteristics	Performances
Minimum thickness:	1,2 mm.
Expected working life:	W3 (25 years)
Climatic zone of use:	S (severe)
User loads:	
Concrete, steel	P4: TH2 // P3: TH4
PU foam	P1:TH2
Roof slope:	S1 ~S4 (≥ 0º)
Minimum surface temperatures:	TL3 (-20ºC)
Maximum surface temperatures:	TH4-TH2
Water tightness:	Watertight
Resistance to wind loads:	Pass (>50kPa)
Concrete	1,9 MPa
Steel	1,6 MPa
PU foam	0,2 MPa (cohesive support)
Resistance to water vapor:	μ = 2.500
Resistance to dynamic indentation:	
Concrete, steel	I4
PU foam	I2
Resistance to static indentation:	
Concrete, steel (250N)	L4
PU foam(70N)	I2
Resistance to fatigue movement:	Pass (1.000 cycles,-10ºC)
Resistance to low-temperature effects (-20ºC):	
Concrete, steel	I4
PU foam	I2
Resistance to high-temperature effects:	
Concrete, steel(250N, 90ºC)	L4
PU foam(70N, 60ºC)	L1
Resistance to heat ageing (200 days at 80ºC):	
Fatigue movement	Pass, (50 cycles, -10ºC)
Dynamic indentation (-20ºC)	
Concrete, steel	I4
PU foam	I1

Tensile strength (initial/ageing)	5/6 MPa
Tensile elongation (initial/ageing)	418/115 %
Resistance to UV-radiation (5000 hours exposed):	
Dynamic indentation	
Concrete, steel	I4
PU foam	I1
Tensile strength (initial/ageing)	5/6 MPa
Tensile elongation (initial/ageing)	418/82 %
Resistance to water ageing (60 days)	
Concrete, steel(250N,90°C)	L4
PU foam(70N,60°C)	L1
Resistance to water ageing(180 days)	
Concrete, steel(250N,60°C)	L4
Concrete, steel(250N,98°C)	L3
Concrete, steel(250N,90°C)	L2
Adherence	Pass ; concrete=1,2MPa
Fire reaction:	NPD
External fire performance:	Broof (t1)+(t4)
Resistance to plant roots:	Resistant
Effects of day joints:	2,1 MPa

<b>7   REACH information</b>	the information referred to Article 31 or, as appropriate, to Article 33 of the REACH Regulation (EC) no. 1907/2006 and following amendments are indicated in the safety data sheet that TECNOPOL makes available on the website along with this current Declaration of Performance
------------------------------	---

The performance of the product identified above is in conformity with the set of declared performances.

This declaration of performance is issued, in accordance with Regulation (EU) no. 305/2011, under the sole responsibility of the manufacturer identified above.

Signed for and on behalf of the manufacturer by: **David Pont – Technical Service Manager**



Les Franqueses del Vallès,

22/01/2021



*DoP in Pdf format are available in the Tecnopol website.*

Revision 0 notes:	First issue
-------------------	-------------

 1219	 <b>TECNOPOL SISTEMAS, S.L.U., Finlàndia, 33 08520 Les Franqueses del Vallès – Barcelona-Spain – <a href="http://www.tecnopolgroup.com">www.tecnopolgroup.com</a></b>																														
<b>21</b> <b>CPR-ES2/0002</b> <b>TECNOCOAT CP-2049 PLUS SYSTEM</b> Two-component polyurea system for intended use as a roof waterproofing																															
<table style="width: 100%; border: none;"> <tr> <td style="width: 35%;">Minimum thickness:</td> <td>1,2 mm.</td> </tr> <tr> <td>Expected working life:</td> <td>W3 (25 years)</td> </tr> <tr> <td>Climatic zone of use:</td> <td>S (severe)</td> </tr> <tr> <td>User loads:</td> <td></td> </tr> <tr> <td style="padding-left: 20px;">Concrete</td> <td>P4: TH2 // P3: TH4</td> </tr> <tr> <td style="padding-left: 20px;">PU foam</td> <td>P1:TH2</td> </tr> <tr> <td>Roof slope:</td> <td>S1 ~S4 (≥ 0º)</td> </tr> <tr> <td>Minimum surface temperatures:</td> <td>TL3 (-20ºC)</td> </tr> <tr> <td>Maximum surface temperatures:</td> <td>TH4-TH2</td> </tr> <tr> <td>Water tightness:</td> <td>Watertight</td> </tr> <tr> <td>Resistance to wind loads:</td> <td>Pass (&gt;50kPa)</td> </tr> <tr> <td>Resistance to water vapor:</td> <td>μ = 2.500</td> </tr> <tr> <td>Fire reaction:</td> <td>NPD</td> </tr> <tr> <td>External fire performance:</td> <td>Broof (t1)+(t4)</td> </tr> <tr> <td>Resistance to plant roots:</td> <td>Resistant</td> </tr> </table>		Minimum thickness:	1,2 mm.	Expected working life:	W3 (25 years)	Climatic zone of use:	S (severe)	User loads:		Concrete	P4: TH2 // P3: TH4	PU foam	P1:TH2	Roof slope:	S1 ~S4 (≥ 0º)	Minimum surface temperatures:	TL3 (-20ºC)	Maximum surface temperatures:	TH4-TH2	Water tightness:	Watertight	Resistance to wind loads:	Pass (>50kPa)	Resistance to water vapor:	μ = 2.500	Fire reaction:	NPD	External fire performance:	Broof (t1)+(t4)	Resistance to plant roots:	Resistant
Minimum thickness:	1,2 mm.																														
Expected working life:	W3 (25 years)																														
Climatic zone of use:	S (severe)																														
User loads:																															
Concrete	P4: TH2 // P3: TH4																														
PU foam	P1:TH2																														
Roof slope:	S1 ~S4 (≥ 0º)																														
Minimum surface temperatures:	TL3 (-20ºC)																														
Maximum surface temperatures:	TH4-TH2																														
Water tightness:	Watertight																														
Resistance to wind loads:	Pass (>50kPa)																														
Resistance to water vapor:	μ = 2.500																														
Fire reaction:	NPD																														
External fire performance:	Broof (t1)+(t4)																														
Resistance to plant roots:	Resistant																														

**Note:**

TECNOPOL SISTEMAS S.L.U, supplies the current annex along with the DoP to make the consultancy of the CE marking easier for the international clients. The enclosed CE marking can be slightly different compared to the one printed on the relevant packaging or documentation because of:

- graphic adaptations due to lack of space on the packaging or printing methods used,
- different language (the same packaging can be shared by several countries),
- the product is already in stock when the updating of the CE marking is implemented,
- printing mistakes